

Mystik® JT-6® Low Temp #2 Grease

Formerly known as Mystik JT-6 Lo-Temp Extreme Grease

OVERVIEW




- Multi-purpose grease for bearings operating in low to medium temperatures, with excellent antiwear protection under high loads.
- For conditions where extremely cold temperatures prevail, minimum friction is necessary, high speeds are involved, excellent rust protection is required, or equipment is stored or used intermittently.
- Considered by many to be the ultimate mining grease due to its ability to lubricate over a wide temperature range.

FEATURES & BENEFITS



- Light-colored, low-staining, and water-resistant.
- Outstanding low-temperature performance.
- Excellent antiwear and extreme pressure protection.
- Water-resistant to seal water out and protect against corrosion.
- Recommended operating temperature range: -40° to 250°F.

APPLICATIONS



- Bearing and chassis applications operating in low to medium temperatures.
- Recommended for use where equipment is stored or used intermittently and excellent rust protection is required.
- Refer to equipment owner's manual for proper lubricant recommendation.

PROPERTIES**Typical Properties for Mystik JT-6 Low Temp #2:**

Material Code	665027002
NLGI Grade	2
Thickener Type	Anhydrous Calcium
Texture	Smooth
Color	Medium Amber
Worked Penetration, ASTM D217	265-295
Dropping Point, ASTM D2265, °F (°C)	285 (140)
Water Washout, ASTM D1264, % loss @ 175°F	5
Rust Prevention, ASTM D1743, rating	Pass
Oil Separation, ASTM D1742, % loss	5
Timken OK Load, ASTM D2509, lb	45
Four-Ball Wear, ASTM D2266, mm	0.56
Four-Ball Weld, ASTM D2596, kgf	315
US Steel Mobility @ 0°F, gpm	540
Low Temperature Torque, ASTM D4693, N-m	0.48
Approximate Temperature Range, °F (°C)	-40° to 250° (-40° to 121°)
Base Oil Viscosity @ 40°C, cSt	20

©2019 CITGO Petroleum Corporation

The Mystik Lubricants name, logo and all related marks are registered trademarks protected by federal law. All other registered trademarks or trademarks are the property of their respective owners.

Values shown are typical values only and do not constitute a specification. The information contained herein is subject to change without notice.